

Property	Unit	Limits		Test Method
		Minimum	Maximum	
Fatty Acid Methyl Ester (FAME) Content	%(V/V)	24	30	EN14078
Water Content	%(m/m)		0.029	EN ISO 12937
Sulfur Content	mg/kg		10	EN ISO 20846
Density at 15°C	kg/m³	825,0	865,0	EN ISO 3675
Cetane Number		51		EN ISO 5165
Polycyclic aromatic hydrocarbons	%(m/m)		8	EN 12916
Manganese Content			2	Pr EN 16576
Flash point	°C	>55.0	-	EN ISO 2719
Ash Content	%(m/m)	-	0.010	EN ISO 6245
Total Contamination	mg/kg	-	24	EN 12662
Oxidation Stability	H	20	-	EN 15751
Viscosity at 40°C	mm²/s	2.000	4.620	EN ISO 3104
Distillation				
% (V/V) recovered at 250°C	%(V/V)		<65	EN ISO 3405
% (V/V) recovered at 350°C	%(V/V)	85		
95% (V/V) recovered at	°C		360	

Climate Dependent Requirements and related Test Methods

Property	Unit	Limits		Test Method
		Grade C*	Grade E**	
CFPP	°C	-5	-15	EN 116

* Argent will supply Grade C from 16th March to the 31st October inclusive.

** Argent will supply Grade E from 1st of November to the 15th March inclusive.

Comments: -

- The above tables use data taken from BS EN 16709.

Issue Status

If printed this document becomes an "uncontrolled copy" and will not be subject to update unless over stamped as a "Controlled Copy"

Page 1 of 1

Page	1
Revision	1
Document	Dieselite B24 to B30 Technical Specification Sheet
Effective Date	28/10/25